

Comment on "Phenomenological model of Dynamic Nonlinear Response in Relaxor Ferroelectrics"

In the recent letter[1] Glazounov and Tagantsev (GT) proposed the phenomenological model of dynamic response of relaxors. The model is based on the well known Landau-Khalatnikov (LK) equation for the polarization dynamics $\partial P/\partial t = -(1/\eta)\partial F/\partial P$, $F(P) = (1/2)\alpha P^2 + (1/4)\beta P^4 - PE$. The new element introduced by the authors is the averaging of the solution of LK equation over the broad distribution of relaxation times $\tau = \eta/\alpha$ which, as the authors assume, resembles the low frequency dispersion of the dielectric response observed in relaxors. The purpose of the present comment is to clarify the physical assumptions involved in the GT approach and show that models based on LK equation can not describe properly the dynamic response in relaxor ferroelectrics.

Note first that LK equation completely ignores all the inhomogeneities of the system both temporal and spatial, and the relaxation time τ is characteristic of the dynamics of the long wave length component of polarization with zero wave vector. The legitimate question to ask in this case is what is the meaning of the averaging over τ proposed by GT? The following scenario might be true. Let us assume that the crystal is divided into macroregions within which the coefficient τ has the same magnitude. Then the average over τ just means the average of the polarization response for different macroregions. However, the above physical picture is very far from the real situation taking place in relaxors, where the existence of nanoscale dynamical inhomogeneities (polar clusters) are well documented. The concept of nanoscale polar clusters provides more natural explanation of the broad distribution of relaxation times in relaxors than that implied by the GT approach. Indeed, each polar cluster may be characterized but its own value of τ with the correlations between the values of τ for different clusters being negligibly small. A formalism which explicitly takes into account the dynamics of interacting polar clusters in relaxors has been developed in Ref[2] and applied successfully to the dielectric experiments in PST and PMN.

We will illustrate below that GT approach leads to the values of the dielectric response which in general is inconsistent with the experiments in relaxors. As follows from GT model, the linear dielectric permittivity may be written in the form

$$\epsilon'(\omega, T) = \epsilon_s(T)(1 - q(\omega, T)) \quad (1)$$

where $1 - q(\omega, T) = \langle 1/(1 + \omega^2 \tau^2) \rangle$, and $\langle \dots \rangle$ denotes the average over τ . It is apparent that the quantity $q(\omega, T)$ is the fraction of polar regions which are effectively frozen on the time scale ω^{-1} . Indeed, if for the major part of

polar regions $\omega\tau \ll 1$, then $q \rightarrow 0$, and in the opposite limit $\omega\tau \gg 1$ $q \rightarrow 1$. Since relaxor ferroelectrics are close to ferroelectric instability they are characterized by a strong increase of the static (field cooled) permittivity $\epsilon_s(T)$ with the temperature decrease. At the same time the frequency dependent permittivity $\epsilon'(\omega, T)$ decreases with temperature below a well defined temperature T_m . The applicability of Eq.(1) in this situation assumes that the increase of ϵ_s is compensated for by an increase of the parameter $q(\omega, T)$. However, recent NMR experiments [3] which obtain direct information on the magnitude of $q(\omega, T)$ from measurements of the inhomogeneous NMR line width do not support this assumption. Indeed, it was found[3] that in PMN, $q \approx 0.2$ at $\omega = 10^5 \text{ Hz}$ and $T=220\text{K}$ which, accordingly to Eq.(1) leads to the conclusion that $\epsilon'(\omega)/\epsilon_s \approx 0.8$. However, dielectric experiments[4] performed in the same sample give a much lower ratio $\epsilon'(\omega)/\epsilon_s < 0.05$ for the same values of the parameters.

This example, accompanied by the given above physical picture of the meaning of the averaging of the solution of the LK equation, clearly shows that GT phenomenological model is inconsistent with the mechanism of relaxor behavior since it does not take into account the existence of short range polar clusters. Therefore, one can doubt the validity for relaxors of the obtained in Ref.[1] expression $P'_3 \sim \beta \epsilon'^3(\omega) \epsilon'(3\omega)$ for nonlinear third order polarization response P'_3 with $\epsilon'(\omega)$ given by Eq.(1). Note, however, that GT employed the above expression for P'_3 only for evaluating the coefficient β using experimental values for both $\epsilon'(\omega)$ and P'_3 . In order to test how sensitive is such a procedure to the particular model we performed the same calculations using the interacting polar clusters model[2]. We obtained

$$P'_3 \sim \beta \epsilon'^3(\omega) \epsilon'(3\omega) (1 - q(3\omega)) / (1 - q(\omega)). \quad (2)$$

Since in relaxors the frequency dependence q is rather weak, such that $q(3\omega) \approx q(\omega)$, one can state that the evaluation of the coefficient β given by GT is quite reliable, although almost with the same degree of accuracy one could have used the expression $P'_3 \sim \beta \epsilon'^4(\omega)$ employed earlier in Ref.[5].

1. A. E. Glazounov and A.K. Tagantsev, PRL **85**, 2192 (2000).
2. B. E. Vugmeister and H. Rabitz, Phys.Rev. B **57**, 7581 (2000); **61**, 14448 (2000).
3. R. Blinc, *et al.*, Phys.Rev.Let. **83**, 424 (1999).
4. A. Levstic, *et al.*, Phys.Rev. B **57**, 11204 (1998).
5. V. Bobnar, *et al.*, Phys.Rev. Lett. **84**, 5892 (2000).

B.E. Vugmeister and H. Rabitz
Department of Chemistry Princeton University
Princeton, NY 08544